

The Thermodynamic Glass Transition in Finite Dimensions

M. A. Moore¹ and J. Yeo²

¹*School of Physics and Astronomy, University of Manchester, Manchester M13 9PL, U. K.*

²*Department of Physics, Konkuk University, Seoul 143-701, Korea*

(Dated: February 2, 2008)

Using an effective potential method, a replica formulism is set up for describing supercooled liquids near their glass transition. The resulting potential is equivalent to that for an Ising spin glass in a magnetic field. Results taken from the droplet picture of spin glasses are then used to provide an explanation of the main features of fragile glasses.

PACS numbers: 64.70.Pf, 75.10.Nr, 75.50.Lk

Structural glasses have been studied extensively at mean-field level by relating them to infinite-range p-spin spin glass models [1]. The dynamical equations of these spin glass models are similar to those of the mode-coupling theory of liquids [2]. These equations predict a dynamical transition at a temperature T_d below which an ergodicity breaking occurs. In the infinite-range p-spin glass models, a discontinuous thermodynamic transition also takes place at a temperature T_K and is usually identified with the Kauzmann glass transition [3]. $T_K < T_d$. It is expected that outside the mean-field limit, there will be no genuine dynamical transition at T_d due to the fact that the metastable states which trap the system dynamically are unstable in finite dimensions because of activation processes over the finite free-energy barriers which separate the metastable states. However, it is commonly assumed that the thermodynamic glass transition T_K could still exist in principle in finite dimensional systems. This paper is essentially an investigation of this question.

We start by constructing an effective Hamiltonian $H[q]$ for supercooled liquids near the putative thermodynamic glass transition in finite dimensions. We find that $H[q]$ is given by the same generic functional which describes the one-step replica symmetry breaking transition [4] for the p-spin spin glass model. Our derivation is based on the effective potential method developed by Franz and Parisi [5] for spin glass models. A similar effective Hamiltonian to ours was used in Refs. [6] and [7] for structural glasses, but not explicitly derived.

The next step is the elucidation of the properties of $H[q]$. There are two coupling constants in the theory, w_1 and w_2 and at mean-field level, the thermodynamic transition is discontinuous (first order) if their ratio w_2/w_1 is greater than one and continuous when less than one. There are arguments for a growing lengthscale in structural glasses as the temperature is reduced ([1], [7], Ref. [6] and references therein, and Bouchaud and Biroli [8]) and experimental evidence for a lengthscale of several interparticle diameters already exists [9]. We feel that it is more natural to study parameters appropriate to the continuous transition rather than the first-order transition in

order to explain a growing lengthscale. Most studies of p-spin models have focussed on parameters which generate the first-order transition to the one-step replica symmetry breaking state, simply because in that situation one also has a mechanism for explaining the dynamical transition T_d . However, it is clear from our derivation of the p-spin functional that the $q_{\alpha\beta}$ in it is not simply related to density fluctuations so our functional cannot be used to directly study dynamical effects in density correlations functions. In our view, they are best determined by mode-coupling theory [2]. Our p-spin functional is appropriate only for the study of the putative glass transition at T_K .

Numerical studies have been performed on a p-spin model with $p = 3$ by Parisi et al. [10], which at mean-field level has a continuous transition [11], (because for it the ratio $w_2/w_1 < 1$). They found a rapidly growing lengthscale in this p-spin model as the temperature was reduced and an attempt was even made to obtain its critical exponents in four dimensions. Moore and Drossel [12] later showed that the continuous transition, if any, would be in the same universality class as the Ising spin glass in a field – the transition usually referred to as the de Almeida-Thouless (AT) transition [13]. However, it has been argued that the AT transition does not actually exist for systems whose dimensionality is less than six [14], but instead there is a crossover line in the field-temperature phase diagram where the growing correlations between the spins saturate. The value of this lengthscale can be estimated from droplet scaling arguments [15]. In the numerical study of Parisi et al. [10] the largest system size studied was of linear dimension six lattice spacings and if the correlation length is larger than the size of the system then the crossover would look like a phase transition. In the work of Moore and Drossel [12] the lengthscale in the (three-dimensional) Migdal-Kadanoff approximation saturated at around 28 lattice spacings at low temperatures. We shall also show using droplet ideas borrowed from spin glasses how this growing lengthscale can produce dynamical behavior of the Vogel-Fulcher type [16].

The calculations start with defining an overlap $p_c(\mathbf{r}) =$

$\delta\rho_1(\mathbf{r})\delta\rho_2(\mathbf{r})$ between two configurations of density fluctuations $\delta\rho = \rho - \langle\rho\rangle$ in two copies of the liquid. By averaging over the density configurations of the first copy while holding the density configurations in the second copy fixed at fixed values of the overlap $p_c(\mathbf{r})$ we obtain a constrained partition function

$$Z[p_c(\mathbf{r}), \delta\rho_2(\mathbf{r})] = \langle \delta(p_c(\mathbf{r}) - \delta\rho_1(\mathbf{r})\delta\rho_2(\mathbf{r})) \rangle_{\rho_1}. \quad (1)$$

The effective potential is given by the average of the free energy with respect to the density configurations in the second copy: $\Omega[p_c(\mathbf{r})] = -T \langle \ln Z[p_c, \delta\rho_2] \rangle_{\rho_2}$. In order to perform the average of the logarithm, we use the replica method and write $\ln Z = \lim_{n \rightarrow 0} (Z^n - 1)/n$. Using the integral representation of the delta function in (1), we can write the effective potential as the following averages over ρ_2 and ρ_1^α ($\alpha = 1, \dots, n$):

$$\Omega[p_c(\mathbf{r})] = -T \int \prod_{\alpha} \frac{\mathcal{D}\lambda_{\alpha}}{2\pi} \exp \left[i \sum_{\alpha} \int d\mathbf{r} \lambda_{\alpha}(\mathbf{r}) p_c(\mathbf{r}) \right] \times \left\langle \left\langle \exp \left[-i \sum_{\alpha} \int d\mathbf{r} \delta\rho_1^{\alpha}(\mathbf{r}) \delta\rho_2(\mathbf{r}) \lambda_{\alpha}(\mathbf{r}) \right] \right\rangle_{\rho_2} \right\rangle_{\rho_1^{\alpha}} \quad (2)$$

We evaluate the above averages over ρ_1^{α} and ρ_2 by making successive cumulant expansions. The resulting integral can be expressed in terms of the liquid-state correlation functions $G(\mathbf{r}_1, \mathbf{r}_2) = \langle \delta\rho(\mathbf{r}_1) \delta\rho(\mathbf{r}_2) \rangle$, $G(\mathbf{r}_1, \mathbf{r}_2, \mathbf{r}_3) = \langle \delta\rho(\mathbf{r}_1) \delta\rho(\mathbf{r}_2) \delta\rho(\mathbf{r}_3) \rangle$, etc. Keeping terms up to $O(\lambda^3)$, we have

$$\begin{aligned} \Omega[p_c(\mathbf{r})] &\simeq -T \int \prod_{\alpha} \frac{\mathcal{D}\lambda_{\alpha}}{2\pi} \exp \left[i \sum_{\alpha} \int d\mathbf{r} \lambda_{\alpha}(\mathbf{r}) p_c(\mathbf{r}) \right] \\ &\times \exp \left[-\frac{1}{2} \int d1 d2 G^2(1, 2) \sum_{\alpha} \lambda_{\alpha}(1) \lambda_{\alpha}(2) \right] \\ &\times \exp \left[\frac{i}{6} \int d1 d2 d3 G^2(1, 2, 3) \sum_{\alpha} \lambda_{\alpha}(1) \lambda_{\alpha}(2) \lambda_{\alpha}(3) \right] \\ &\times \exp [O(\lambda_{\alpha}^4, \lambda_{\alpha}^2 \lambda_{\beta}^2)], \end{aligned} \quad (3)$$

where $1, 2, \dots$ denote the position vectors $\mathbf{r}_1, \mathbf{r}_2, \dots$.

Now we define $q_{\alpha\beta}(\mathbf{r}) = \lambda_{\alpha}(\mathbf{r})\lambda_{\beta}(\mathbf{r})$ for $\alpha \neq \beta$ and write the effective potential as a functional integral of the fields $q_{\alpha\beta}$. We insert the following identity inside the above expression:

$$1 = \int \prod_{\alpha < \beta} \mathcal{D}q_{\alpha\beta} \int \prod_{\alpha < \beta} \frac{\mathcal{D}u_{\alpha\beta}}{2\pi} \times \exp \left[i \sum_{\alpha < \beta} \int d\mathbf{r} u_{\alpha\beta}(\mathbf{r}) (q_{\alpha\beta}(\mathbf{r}) - \lambda_{\alpha}(\mathbf{r})\lambda_{\beta}(\mathbf{r})) \right]. \quad (4)$$

Due to the coupling between λ_{α} and $u_{\alpha\beta}$, the integration over λ_{α} generates various terms in $u_{\alpha\beta}$. For example, to the lowest order, the quadratic term in $u_{\alpha\beta}$ comes from

joining two pairs of λ 's in the two $u\lambda\lambda$ vertices. Therefore the coefficient of the quadratic term in $u_{\alpha\beta}$ involves, to the lowest order, the square of the λ -propagator $K(1, 2)$ satisfying

$$\int d3 K(1, 3) [G^2(3, 2)] = \delta(12). \quad (5)$$

There are, of course, other contributions to the $O(u^2)$ term, which come from the higher order vertices in λ . These just renormalize its coefficient. Two kinds of cubic terms in $u_{\alpha\beta}$ are generated, namely, $\text{Tr } u^3$ and $\sum u_{\alpha\beta}^3$. The coefficients of these terms will contain in general the contributions from the higher order vertices in λ . Keeping up to the cubic order in $u_{\alpha\beta}$, we have

$$\begin{aligned} \Omega[p_c(\mathbf{r})] &\sim -T \int \prod_{\alpha < \beta} \mathcal{D}q_{\alpha\beta} \int \prod_{\alpha < \beta} \frac{\mathcal{D}u_{\alpha\beta}}{2\pi} \\ &\times \exp \left[i \sum_{\alpha < \beta} \int d\mathbf{r} u_{\alpha\beta}(\mathbf{r}) q_{\alpha\beta}(\mathbf{r}) \right] \\ &\times \exp \left[\frac{i}{2} \sum_{\alpha < \beta} \int d1 d2 d3 A(1, 2, 3) u_{\alpha\beta}(1) p_c(2) p_c(3) \right] \\ &\times \exp \left[-\frac{1}{2} \sum_{\alpha < \beta} \int d1 d2 B(1, 2) u_{\alpha\beta}(1) u_{\alpha\beta}(2) \right] \\ &\times \exp \left[\frac{i}{6} \sum_{(\alpha, \beta, \gamma)} \int d1 d2 d3 C(1, 2, 3) u_{\alpha\beta}(1) u_{\beta\gamma}(2) u_{\gamma\alpha}(3) \right] \\ &\times \exp \left[\frac{i}{6} \sum_{\alpha < \beta} \int d1 d2 d3 D(1, 2, 3) u_{\alpha\beta}(1) u_{\alpha\beta}(2) u_{\alpha\beta}(3) \right], \end{aligned} \quad (6)$$

where we dropped the terms in p_c which do not couple to $u_{\alpha\beta}$. The coefficients A, B, C and D are given, to the lowest order, by

$$A(1, 2, 3) \simeq K(1, 3)K(2, 3), \quad (7)$$

$$B(1, 2) \simeq K^2(1, 2), \quad (8)$$

$$C(1, 2, 3) \simeq K(1, 2)K(2, 3)K(3, 1), \quad (9)$$

$$D(1, 2, 3) \simeq - \int \prod_{i=4}^9 d\mathbf{r}_i G^2(4, 5, 6) G^2(7, 8, 9) \times K(1, 4)K(1, 7)K(2, 5)K(2, 8)K(3, 6)K(3, 9). \quad (10)$$

Finally we integrate over $u_{\alpha\beta}$ to obtain the effective Hamiltonian in terms of $q_{\alpha\beta}$ as follows. First note that in addition to the usual quadratic term in $q_{\alpha\beta}$, there are cubic terms in q in the form $\text{Tr } q^3$ and $\sum q_{\alpha\beta}^3$ with real coefficients. We also note that the terms involving p_c couple to $q_{\alpha\beta}$ in the form $p_c^{2k} q_{\alpha\beta}^{k'}$ with integers k and k' . The resulting expression gives the effective potential $\Omega[p_c]$ in terms of a functional integral over the fields $q_{\alpha\beta}$. Since the value of the overlap is determined from the condition $\delta\Omega/\delta p_c = 0$, $p_c(\mathbf{r}) = 0$ is always a solution and describes the liquid phase. We take the effective Hamiltonian $H[q]$ for supercooled liquids as

$\Omega[p_c = 0] \sim \int \prod_{\alpha < \beta} \mathcal{D}q_{\alpha\beta} \exp[-H[q]]$. The coefficients of various terms in $q_{\alpha\beta}$ in $H[q]$ are in general expressed in a nonlocal way much like Eqs. (7)-(10). However, the most relevant terms will be the local ones where all the points in space are the same. Keeping as usual the derivative term only in the quadratic order in $q_{\alpha\beta}$, we obtain the effective Hamiltonian as

$$H[q] = \int d\mathbf{r} \left\{ \frac{c}{2} \sum_{\alpha < \beta} (\nabla q_{\alpha\beta}(\mathbf{r}))^2 + \frac{t}{2} \sum_{\alpha < \beta} q_{\alpha\beta}^2(\mathbf{r}) - \frac{w_1}{6} \text{Tr} q^3(\mathbf{r}) - \frac{w_2}{3} \sum_{\alpha < \beta} q_{\alpha\beta}^3(\mathbf{r}) \right\}. \quad (11)$$

The coefficients c, t, w_1 and w_2 will be functions of the temperature and density of the liquid, with smooth dependence on them. The study of the first-order transition which occurs at mean-field level requires the inclusion of terms quartic in the $q_{\alpha\beta}$ fields, but these are ‘irrelevant’ variables at the presumed continuous transition in finite dimensions and they will be dropped. At mean-field level, the transition is continuous if $w_2/w_1 \leq 1$ [4]. In the p-spin replicated functional of Eq. (11) the coefficients in it have contributions from all the higher order cumulants of the density etc.. Fortunately as we are studying a continuous transition, their numerical values will only effect non-universal features of the putative transition.

The thermal average $\langle q_{\alpha\beta} \rangle$ is non-zero even above any supposed transition (when one goes beyond the mean-field approximation) because of the term in w_2 in the Hamiltonian of Eq. (11). As a consequence the only possible continuous phase transition is one which breaks the replica symmetry of the high-temperature phase. This transition was shown in Ref. [12] to be in the same universality class as that for the transition from the paramagnet to the spin glass phase in a field, first discussed by de Almeida and Thouless [13]. The Hamiltonian of an Ising spin glass in a field is

$$\mathcal{H} = - \sum_{\langle ij \rangle} J_{ij} S_i S_j - h \sum_i S_i. \quad (12)$$

The couplings J_{ij} are quenched random variables connecting (usually) nearest-neighbor sites. The Edwards-Anderson order parameter is $\tilde{q} = \sum_i \langle S_i \rangle^2 / N$ and in zero field becomes non-zero below T_s , the critical temperature of the zero-field spin glass transition. Using the replica method one can set up a functional analogous to that for structural glasses in Eq. (11) for the spin glass Hamiltonian [17]. It differs only in that the cubic term $(w_2/3) \sum q_{\alpha\beta}^3$ is absent but there is instead a linear term $h^2 \sum q_{\alpha\beta}$. Now when the temperature T is in the vicinity of the thermodynamic structural ‘glass transition’ T_K , we expect it to be well below T_s . At such temperatures w_2 and h^2 can be related by noting that the cubic term could be approximated by $w_2 \sum \langle q_{\alpha\beta}^2 \rangle q_{\alpha\beta}$. $\langle q_{\alpha\beta}^2 \rangle$ will be independent of α and β as we are working in the replica

symmetric phase, and only slowly varying as a function of temperature so then $h^2 \propto w_2$. Then because w_2 is a function of the temperature and density of the liquid, h^2 in the Ising spin glass analogue will also be a temperature and density-dependent quantity.

The question then of whether there is or is not a structural glass transition then turns on whether there is an AT line in the spin glass analogue. This has been controversial in the past, but numerical [18] and experimental data [19] favors its absence in three dimensional spin glasses and we further argued in Ref. [14] that for all dimensions $d < 6$ there would be no AT line. We shall henceforth take it that there is no AT line and hence that there is no thermodynamic glass transition for three dimensional systems. How then can we explain the phenomena normally associated with the glass transition?

The key to understanding this point is to realize that even if there is no AT line there can be a growing length-scale as the temperature is reduced. The lengthscale is analogous to the ‘mosaic’ lengthscale of other authors [1, 6, 7, 8], but its physical origin is different. In our case, the lengthscale is equal to the size of the droplet in the spin glass analogue which is typically flipped by the application of the field h . To flip a region of size L in the low-temperature phase of a spin glass typically costs an ‘interface’ free energy of order $(L/\xi(T))^\theta$, where $\xi(T)$ is the correlation length associated with the spin glass transition in zero-field and θ is an exponent typically ~ 0.2 [15]. Each droplet has a magnetic moment of order $\sqrt{q} L^{d/2}$ so in a field of magnitude h the domains are of size L^* , where

$$(L^*/\xi(T))^\theta \sim \sqrt{q}(L^*)^{d/2}h, \quad (13)$$

in order that the energy gained by flipping a droplet in the field h just balances the interface free energy cost. This result for L^* should be valid provided $L^* > \xi(T)$.

In the droplet picture the free-energy barrier which has to be surmounted in order to flip a region of size L^* is $A(L^*/\xi(T))^\psi$, where A is of order of the critical temperature T_s [15]. The basic relaxation time τ in the system is of Arrhenius form:

$$\tau \sim \tau_0 \exp[A(L^*/\xi(T))^\psi/T]. \quad (14)$$

Alas, the value of ψ in three dimensional spin glasses is very poorly determined, with quoted values varying widely.

When $T \ll T_s$, $\xi(T)$ will be a slowly varying function of temperature and of order of the interparticle spacing. $\tilde{q}$ will also then be nearly temperature-independent. If w_2 is only weakly temperature dependent, L^* will be approximately temperature independent and τ will then be of the simple Arrhenius form. This will be the case then of strong glasses. For fragile glasses we expect that

$$w_2 \sim h^2 \sim (T - T_0), \quad (15)$$

so that w_2 appears to be going to zero at T_0 . We stress that the effective value of w_2 probably will never vanish, since even if the bare coefficient did go to zero the higher terms in the functional $H[q]$ which break the time-reversal invariance will make its effective value non-zero so Eq. (15) is just a simple phenomenological way to obtain a growing lengthscale. Then

$$\tau \sim \tau_0 \exp \left[\frac{C}{(T - T_0)^{\frac{\psi}{d-2\theta}}} \right], \quad (16)$$

where C denotes a constant. It is clear that this has similarities to the Vogel-Fulcher [16] form for structural relaxation times in the supercooled liquid:

$$\tau \sim \tau_0 \exp \left[\frac{C}{T - T_0} \right]. \quad (17)$$

Note that we have proceeded on the assumption that the exponent ψ for the supercooled liquid and the spin glass are the same. In principle our mapping between liquids and spin glasses is explicit only for ‘equilibrium’ quantities and might not extend to dynamical features. Note that the droplet formula for τ of Eq. (14) is only expected to hold when L^* is much larger than the typical distance between the molecules of the glass, and experiments might not have reached the region where it has become valid; in other words the simple exponent of the Vogel-Fulcher fit might reflect pre-asymptotic behavior.

The simulations of Parisi et al. [10] show that the entropy per spin went to zero apparently as $s_c(T) \approx k_B(T - T_K)$, although no data was obtained close to T_K and without a genuine transition the entropy is unlikely to ever vanish completely. A similar behavior is found for the configurational entropy per particle in fragile glasses. What is striking about the simulations is that the temperature T_K was very close to the temperature T_0 at which the correlation length was apparently diverging (the difference was less than 1%). One feature common to fragile glasses is that for most of them T_0 extracted from the Vogel-Fulcher fit is close to the Kauzmann temperature T_K , the temperature at which the extrapolated entropy of the supercooled liquid apparently falls to that of the crystalline phase. The ratio T_K/T_0 lies between 0.9–1.1 for many glass formers amongst which T_K ranges from 50 K to 1000 K [20]. Since we are arguing that there is no genuine transition but only a crossover, the ‘ T_0 ’ obtained from the timescale τ , the T_0 of Eq. (15) and T_K need not be precisely the same.

We should like to acknowledge the hospitality of the Korea Institute for Advanced Study during the prepara-

tion of this paper. We are indebted to Drs G. Biroli and J-P Bouchaud for their comments and insights.

-
- [1] T. R. Kirkpatrick and P. G. Wolynes, Phys. Rev. A **35**, 3072 (1987); T. R. Kirkpatrick and D. Thirumalai, Phys. Rev. B **36**, 5388 (1987); T. R. Kirkpatrick and P. G. Wolynes, Phys. Rev. B **36**, 8552 (1987).
 - [2] W. Götze and L. Sjögren Rep. Prog. Phys **55**241 (1992); W. Götze in *Liquid, Freezing and the Glass Transition*, edited by J. P. Hansen, D. Levesque and J. Zinn-Justin, (Elsevier, New York, 1991); J. P. Bouchaud, L. F. Cugliandolo, J. Kurchan and M. Mezard in *Spin Glasses and Random Fields*, edited by A. P. Young, (World Scientific, Singapore, 1997).
 - [3] W. Kauzmann, Chem. Rev. **43**, 219 (1948).
 - [4] M. E. Ferrero, G. Parisi and P. Ranieri, J. Phys. A **29**, L569 (1996).
 - [5] S. Franz and G. Parisi, Phys. Rev. Lett. **79**, 2486 (1997); J. Phys. I (France) **5**, 1401 (1995).
 - [6] M. Dzero, J. Schmalian and P. G. Wolynes, cond-mat/0502011.
 - [7] S. Franz, J. Stat. Mech. P04001 (2005); S. Franz, cond-mat/0507585.
 - [8] J. P. Bouchaud and G. Biroli, J. Chem. Phys. **121**, 7347 (2004).
 - [9] L. Berthier, G. Biroli, J-P. Bouchaud, L. Cipelletti, D. El Masri, D. L’Hôte, F. Ladieu, and M. Pierno, Science **310**, 1797 (2005).
 - [10] G. Parisi, M. Picco and F. Ritort, Phys. Rev. E **60**, 58 (1999).
 - [11] M. A. Moore and J. Yeo, unpublished.
 - [12] M. A. Moore and B. Drossel, Phys. Rev. Lett. **89**, 217202 (2002).
 - [13] J. R. L. de Almeida and D. J. Thouless, J. Phys. A **11**, 983 (1978).
 - [14] M. A. Moore, J. Phys. A **38**, L783 (2005).
 - [15] A. J. Bray and M. A. Moore, in *Glassy Dynamics and Optimization*, edited by J. L. van Hemmen and I. Morgenstern, (Springer, Berlin, 1986); D. S. Fisher and D. A. Huse, Phys. Rev. Lett. **56**, 1601 (1986); Phys. Rev. B **38**, 386 (1988); W. L. McMillan, J. Phys. C **17**, 3179 (1984).
 - [16] For recent papers see P. G. Debenedetti and F. H. Stillinger, Nature **410**, 259 (2001); M. A. Ediger Annual Rev. Phys. Chem. **51**, 99 (2000).
 - [17] A. J. Bray and S. A. Roberts, J. Phys. C **13**, 5405 (1980).
 - [18] A. P. Young and H. G. Katzgraber, Phys. Rev. Lett. **93**, 207203 (2004).
 - [19] J. Mattson, T. Jonsson, P. Nordblad, H. Aruga Katori and A. Ito, Phys. Rev. Lett. **74** 4305 (1995).
 - [20] C. A. Angell, Jour. Res. NIST, **102**, 171 (1997); R. Richert and C. A. Angell, J. Chem. Phys. **108**, 9016 (1998).